

STANDARD AND MINI SPLIT LINE SETS FOR HVACR APPLICATIONS

Job Name	Contractor
Job Location	Wholesaler
Engineer	Streamline[®] Rep

Product Description:

Streamline[®] Standard and Mini Split Line Sets are available in either an elastomeric or polyethylene insulation for use in HVACR applications. All line sets will be manufactured in the United States.

Material:

Streamline[®] Standard and Mini Split Line Sets copper tube shall be made from C12200 grade of copper. Insulation is choice of elastomeric or polyethylene material. Both insulation types have a UV retardant.


Key Specifications:


Streamline[®] Copper Tube is UL Recognized to 700 PSI and can be used with synthetic refrigerants and sub-critical CO2 systems.

Installation:

Installations and insulation material shall comply with the latest applicable building codes for the local jurisdiction.

References:

Product Line	Product Type	Diameter
Copper Tube 	Streamline [®] Refrigeration Service Coils	1/8" – 1-1/8"
	Streamline [®] Line Sets & Mini-Splits	1/8" – 1-1/8"
	Streamline [®] ACR - Type L (Hard Lengths)	1/8" – 1-3/8"
	Streamline [®] ACR - Type K (Hard Lengths)	1/8" – 2-5/8"



STANDARD AND MINI SPLIT LINE SET DATA

STANDARD LINE SETS WITH ELASTOMERIC INSULATION

HRF Max	Copper Tube Sizes		Lengths	Insulation Thickness	Optional Finishes
	Liquid Line	Suction Line			
50	1/4" - 1/2"	3/8" - 1-1/8"	10' - 50' using 5' intervals; 60' & 100' (other lengths are available upon customer request)	3/8" - 1"	Flare nuts, 90-degree bends, custom connections, thermostat wire and taping

MINI SPLIT LINE SETS WITH ELASTOMERIC INSULATION

HRF Max	Copper Tube Sizes		Lengths	Insulation Thickness	Optional Finishes
	Liquid Line	Suction Line			
50	1/4" - 3/8"	3/8" - 3/4"	15' - 50' using 5' intervals; 100' (other lengths are available upon customer request)	3/8" - 1"	Insulated liquid and suction lines and twin tube system, flare nuts, 90-degree bends, custom connections, mini-split wire or control cable and taping

DURAGUARD™ PE LINE SETS WITH POLYETHYLENE INSULATION

HRF Max	Copper Tube Sizes	Lengths	Insulation Thickness
50	1/4" - 7/8"	35', 50', 100', 164' (insulation marked every foot)	1/2" - 3/4"

ELASTOMERIC INSULATION SPECIFICATION

INSULATION:

"R" Values

Pipe Insulation ID Size	Nom. 3/8"	Nom. 1/2"	Nom. 3/4"	Nom. 1"
3/8"	2.5	3.2	5.4	-
1/2"	2.4	3.2	5.2	-
5/8"	2.3	3.2	5.2	6.7
3/4"	2.2	3.1	5.1	6.5
7/8"	2.2	3.1	5.0	6.5
1-1/8"	2.1	3.0	5.4	6.8

SPECIFICATION COMPLIANCE

- ASTM B1003
- ASTM C 534, Type II —
Sheet Grade I
- ASTM C 1534
- ASTM E 84, NFPA 255, U L 723
- CAN/ULC S102
- NFPA 90A, 90B
- ASTM G21/C1338
- ASTM G22
- ASTM D 1056, 2B1
- MIL-P-15280J, FORM S
- MIL-C-3133C (MIL STD 670B),
Grade SBE 3
- MEA 107-89M
- UL 181
- UL 94 5V-A, V-0, File E 55798
- City of Los Angeles – RR 7642
- ASTM D 1149

PHYSICAL PROPERTIES

Specifications	Values	Test Method
Thermal Conductivity, Btu • in./h • ft ² • °F (W/mK)		
75°F Mean Temperature (24°C)	0.25 (0.036)	
90°F Mean Temperature (32°C)	0.256 (0.037)	ASTM C 177 or C 518
Water Vapor Permeability, Perm-in. [Kg/(s•m•Pa)]	0.05 (0.725 x 10 ⁻¹³)	ASTM E 96, Procedure A
Flame Spread and Smoke Developed Index through 1" (25mm)*	25/50*	ASTM E 84 CAN/ULC S102
Mold Growth	UL181	Meets requirements
Fungi Resistance	ASTM G21/C1338	Meets requirements
Bacterial Resistance	ASTM G22	Meets requirements
Water Absorption, % by Volume	180/220°F (82/105°C)	ASTM C 209
Upper Use Limit	220°F (104°C)	—
Lower Use Limit	-297°F (-183°C)**	—
Ozone Resistance	GOOD	ASTM D 1149

POLYETHYLENE INSULATION SPECIFICATION

Insulation:

Wall thickness is 1/2" - 3/4" and product is made according to ASTM C 1427-07 (insulation material for use on typical commercial system non-cross-linked)

“R” Value:

1/2" Wall = R3

3/4" Wall = R5

Taping of tube and insulation ends is recommended for all installations of Duraguard with PE insulation. Both ends of the tube should be taped with 2" wide Polyken-936-30 tape or equivalent (high U.V. Resistant/High tack joint wrap tape).

SPECIFICATION COMPLIANCE

Description	Specifications	Notes
Water Vapor Permeability	ASTM E96-00	$r = 4 \times 10^{-5}$ [mg/(h*m*Pa)]
Working Temperature	ASTM C 1427-07	Type I (tubular), Grade I
Surface Burning Characteristics	ASTM E84 (25/50)	Flame & Spread Index Less Than 25 & Smoke Development Index less than 50
Thermal Conductivity	ASTM C 335-95	“k” at 104°F (average temperature) = 0.263468 (Btu in.)/sq.ft. °F h)
	ISO EN 8497	“λ” at 40 °C (average temperature) = 0.038 W/(m*K)

WARNING: This product includes polyethylene (PE) foam insulation. Although this product meets ASTM E84 25/50 flame/smoke index, PE foam insulation may nonetheless be highly flammable when ignited. To reduce the risk of fire spread, property damage, or personal injury, great caution should be exercised when using this product in proximity to any ignition sources or open flames.